

## ECOTURF GREEN DIVOT SAND SPEC

Blended and Distributed from Strathmore, AB

SUPPLIER: Target Technologies International Inc  
 GRADATION: 30-50

**COATING PHYSICAL PROPERTIES:**

Non microplastic acrylic coating  
 UV resistant  
 Stain resistant  
 Water resistant  
 Antimicrobial APEO Free, formaldehyde free, low VOC

**SAND PHYSICAL PROPERTIES:**

Agglomerated: No  
 Shape: sub round to round  
 Sphericity: 0.75 to 0.85  
 Roundness: 0.6 to 0.7  
 Mohs Hardness: 7  
 Dust: Negligible  
 Crush Resistance: less than 10

**TESTING:**

- EPA 1633 PFAS Testing
- ASTM F3188 Toxicology
- EN-71-3 Toxicology
- EPA6020B CAM 17 Toxicology
- PAH's Toxicology
- Lisport

**MIN/MAX LEVELS**

Sieve Size	% Retained
ASTM	30-50
No. 16	-
No. 20	0-1
No. 25	-
No. 30	4-8
No. 35	-
No. 40	50-75
No. 45	10-20
No. 50	5-15
No. 70	1-4
Pan	0-1